

## SPRAY GUN AND SET UP DATA SELECTOR: Gun Inlet Pressure 2.0 bar/29 psi



PRi Filler/Primer Gun



GTi Topcoat Gun



GTiW Basecoat Gun



SRi Spot Repair - Topcoats



SRiW Spot Repair - Basecoats

		Air Cap No:	310 (Trans-Tech)	110 (Trans-Tech)	115 (HVLP)	210 (Trans-Tech)	No 215 (HVLP)
<b>WASH PRIMERS</b>			1.6 mm	Use PRi Gun	Use PRi Gun	0.8 - 1.0 mm	Use SRi Gun
<b>1K PRIMER/FILLERS</b>			Use GTi Gun	1.3 - 1.4 mm	Use GTi Gun	1.0 - 1.2 mm	Use SRi Gun
<b>EPOXY PRIMERS</b>			1.6 - 1.8 mm	1.3 - 1.4 mm	Do Not Use	1.0 - 1.2 mm	Use SRi Gun
<b>SURFACERS</b>	2K		1.6 - 1.8 mm	Use PRi Gun	Use PRi Gun	1.0 - 1.2 mm	Use SRi Gun
	MS		1.6 - 1.8 mm	Use PRi Gun	Use PRi Gun	1.0 - 1.2 mm	Use SRi Gun
	HS		1.6 - 1.8 mm	Use PRi Gun	Use PRi Gun	1.0 - 1.2 mm	Use SRi Gun
<b>NON SANDING FILLERS</b>	MS		Use GTi Gun	1.3 - 1.4 mm	Use GTi Gun	1.0 - 1.2 mm	Use SRi Gun
	HS		Use GTi Gun	1.3 - 1.4 mm	Use GTi Gun	1.0 - 1.2 mm	Use SRi Gun
<b>TOP COATS</b>	2K		Use GTi Gun	1.3 - 1.4 mm	Use GTi Gun	0.8 - 1.0 mm	Use SRi Gun
	MS		Use GTi Gun	1.3 - 1.4 mm	Use GTi Gun	0.8 - 1.0 mm	Use SRi Gun
	HS		Use GTi Gun	1.3 - 1.4 mm	Use GTi Gun	0.8 - 1.0 mm	Use SRi Gun
	Synthetic		Use GTi Gun	1.3 - 1.4 mm	Use GTi Gun	0.8 - 1.0 mm	Use SRi Gun
<b>WATERBORNE BASECOAT</b>			Do Not Use	1.3 mm	1.3 mm	0.8 - 1.0 mm	1.0 mm
<b>SOLVENTBORNE BASECOAT</b>			Do Not use	1.3 mm	Use GTi Gun	0.8 - 1.0 mm	Use SRi Gun
<b>CLEARCOAT</b>	2K		Use GTi Gun	1.3 - 1.4 mm	Use GTi Gun	1.0 - 1.2 mm	Use SRi Gun
	MS		Use GTi Gun	1.3 - 1.4 mm	Use GTi Gun	1.0 - 1.2 mm	Use SRi Gun
	HS		Use GTi Gun	1.3 - 1.4 mm	Use GTi Gun	1.0 - 1.2 mm	Use SRi Gun
	Synthetic		Use GTi Gun	1.3 - 1.4 mm	Use GTi Gun	1.0 - 1.2 mm	Use SRi Gun

## SPRAY GUN AND SET UP DATA SELECTOR: Gun Inlet Pressure 2.0 bar/29 psi



PRi Filler/Primer Gun



GTi Topcoat Gun



GTiW Basecoat Gun



SRi Spot Repair - Topcoats



SRiW Spot Repair - Basecoats

VOC COMPLIANT		Air Cap No:	310 (Trans-Tech)	110 (Trans-Tech)	115 (HVLP)	210 (Trans-Tech)	No 215 (HVLP)
PRIMERS	Washprimer 1-15		1.6 mm	Use PRi Gun	Use PRi Gun	0.8 - 1.0 mm	Use SRi Gun
	Washprimer 1-17 CH		1.6 mm	Use PRi Gun	Use PRi Gun	0.8 - 1.0 mm	Use SRi Gun
	1K kunstofprimer 1-60		Use GTi Gun	1.3 - 1.4 mm	Use GTi Gun	0.8 - 1.0 mm	Use SRi Gun
PRIMER/ SURFACER	Epoxy Primer 1-75 Epoxy Primer 1-7510		1.6 - 1.8 mm	1.3 - 1.4 mm	Use SRi/GTi	1.0 - 1.2 mm	Use SRi Gun
	HS Surfacer 8-145 8-14510/8-14540		1.6 - 1.8 mm	Use PRi Gun	Use PRi Gun	1.0 - 1.2 mm	Use SRi Gun
	HS Non Sanding Filler 30-746		1.6 mm	1.3 - 1.4 mm	Do Not Use	1.0 - 1.2 mm	Use SRi Gun
WATERBORNE BASECOAT	Waterbase Serie 900		Do Not Use	1.3 mm	1.3 mm	0.8 - 1.0 mm	1.0 mm
CLEARCOATS	HS Clearcoat 8-104		Do Not Use	1.3 - 1.4 mm	Use GTi Gun	1.0 - 1.2 mm	Use SRi Gun
	HS 420		Do Not Use	1.3 - 1.4 mm	Use GTi Gun	1.0 - 1.2 mm	Use SRi Gun