

Glasurit. Finish First



PRI Filler/Primer Gun



GTI Topcoat Gun



GTIW Basecoat Gun



SRI Spot Repair - Topcoats



SRIW Spot Repair - Basecoats

Air Cap No:		310 (Trans-Tech)	110 (Trans-Tech)	115 (HVLP)	210 (Trans-Tech)	No 215 (HVLP)
PRIMERS & PRIMERFILLERS	285-16 2K Thermo Primer Filler	1.6 - 1.8 mm	Use PRI Gun	Use PRI Gun	0.7 mm	0.7 mm
	285-50 2K HS Primer Filler	1.6 - 1.8 mm	Use PRI Gun	Use PRI Gun	0.7 mm	0.7 mm
	285-60 2K HS Primer Filler (wet/dry sand)	1.6 - 1.8 mm	Use PRI Gun	Use PRI Gun	0.7 mm	0.7 mm
	285-95 2K HS Tintable Filler (high build only)	1.6 - 1.8 mm	Use PRI Gun	Use PRI Gun	0.7 mm	0.7 mm
	285-95 2K HS Tintable Filler (wet on wet only)	Do Not Use	1.3 mm	1.3 mm	0.7 mm	0.7 mm
	76-71 Waterbased 1K Primer Filler	1.6 - 1.8 mm	Use PRI Gun	Use PRI Gun	0.7 mm	0.7 mm
PRIMER SURFACERS	934-70 Plastics Primer	1.6 - 1.8 mm	Use PRI Gun	Use PRI Gun	0.7 mm	0.7 mm
TOPCOAT DIRECT GLOSS	22 Line HS 2K Topcoat	Do Not Use	1.3 mm	1.3 mm	0.7 mm	0.7 mm
	22 Line HS 2K Topcoat 3.5 VOC	Do Not Use	1.3 mm	1.3 mm	0.7 mm	0.7 mm
BASECOAT	90 Line Waterborne Basecoat	Do Not Use	Do Not Use	1.3 mm	Do Not Use	0.7 mm

Glasurit. Finish First



PRI Filler/Primer Gun



GTi Topcoat Gun



GTiW Basecoat Gun



SRi Spot Repair - Topcoats



SRiW Spot Repair - Basecoats

Air Cap No:		310 (Trans-Tech)	110 (Trans-Tech)	115 (HVLP)	210 (Trans-Tech)	No 215 (HVLP)
BASECOAT cont.	55 Line Solvenborne Basecoat	Do Not Use	1.3 mm	1.3 mm	Do Not Use	0.7 mm
CLEARCOATS	923-35 Clear 3.5 VOC	Do Not Use	1.3 mm	1.3 mm	0.7 mm	0.7 mm
	923-255 HS Multi Clear	Do Not Use	1.3 mm	1.3 mm	0.7 mm	0.7 mm
	923-144 MS Racing Clear	Do Not Use	1.3 mm	1.3 mm	0.7 mm	0.7 mm
	923-155 MS Clear	Do Not Use	1.3 mm	1.3 mm	0.7 mm	0.7 mm